



## GRANULAR ACTIVATED CARBON CR830D

CR830D is a granular activated carbon produced from select bamboo wood by a high temperature activation process under stringent quality control. It has a large surface area, high mechanical hardness, excellent pore volume, with unique distribution of pore sizes.

### FEATURES AND BENEFITS

- ◆ High adsorption capacity and efficiency
  - ◆ Hard and durable
  - ◆ Highly developed pore structure

---

### SPECIFICATIONS

Mesh Size:	
Greater than 8	5%
Less than 30	5%
Iodine Number (mg/g)	950 minimum
Methylene Blue (mg/g)	150 minimum
Hardness Number	90 minimum
Moisture (as packed)	5% maximum
Ash Content	6%
Ph	9
Bulk Density (cm <sup>3</sup> /g)	0.40 typical

---

Packaged in 44-lb. bags or 850-lb. super sacks.  
All of the above test methods are performed using AWWA and ASTM protocol for activated carbon.

This information has been gathered from standard reference materials and/or test data that is assumed to be accurate and reliable. Carbon Resources, LLC, only warrants that this product will meet the above described published specifications and makes no other warranties of any kind either expressed or implied including but not limited to fitness for a particular purpose or application. Buyer assumes all liability and risk that may arise from the use of this product.